(07791) 79, Magokjungang 8-ro 3-gil, Gangseo-gu, Seoul
Tel : 02-3299-8000 Fax : 02-3299-8153

TEST REPORT

APPLICANT : SHIN SUNG CO., LTD.

REPORT NO.	: H214-20-03979
SAMPLE RECEIVED DATE	: 2020-05-13
TEST STARTED DATE	: 2020-05-13
REPORT ISSUED DATE	: 2020-05-15
PAGE	: 1 OF 3

DESCRIPTION : TWO(2) PIECES OF SUBMITTED CUTTING SAID TO BE WEBBING.

==========

BUYER'S NAME : [redacted]
ITEM : #1 NN019 1" TENNIS #242 W/REFLECTIVE
#2 NN019 1" DARK OLIVE #315 W/REFLECTIVE

==========

TEST CONDUCTED : AS REQUESTED BY THE APPLICANT, FOR DETAILS PLEASE SEE ATTACHED PAGES.

==========

PREPARED AND CHECKED BY
FOR FITI

HYUN-JIN, KOO
QUALITY MANAGER

AUTHORIZED BY
FOR FITI

JE-GOO JUN
PRESIDENT

※ Report Verification No.: [redacted]
(You can see the authenticity of your test report through the above "Report Verification No." at FITI homepage.)

e-DOCUMENT SERVICE

The test results contained in this report are limited to results on the sample(s) that is provided by client and are not necessarily indicative or representative of the qualities of the lot from which the sample(s) was taken or of all products. Results contained in this report are not based on the quality certification of sample by the FITI quality certification program unless specifically requested by the client. Further use of the results of this report is prohibited unless allowed under a separate agreement set forth in an official document that is established between the client identified on this letter and the FITI.
This test report is irrelevant to KS Q ISO/IEC 17025 and KOLAS accreditation.

(07791) 79, Magokjungang 8-ro 3-gil, Gangseo-gu, Seoul
Tel : 02-3299-8000 Fax : 02-3299-8153

01. COLORFASTNESS TO WASHING (AATCC TM61-2013e2 : 2013, TEST NO. 2A, 45 MINUTES MECHANICAL WASH AT (49 ± 2)℃, IN 0.15 % AATCC WOB DETERGENT SOLUTION WITH 50 STEEL BALLS) : GRADE

	#1	#2
COLOR CHANGE	4.5	4.5
COLOR STAINING		
- ACETATE	4.5	4.5
- COTTON	4.5	4.5
- NYLON	4.5	4.5
- POLYESTER	4.5	4.5
- ACRYLIC	4.5	4.5
- WOOL	4.5	4.5

02. COLORFASTNESS TO WATER (AATCC TM107-2013e2 : 2013) : GRADE

	#1	#2
COLOR CHANGE	4.5	4.5
COLOR STAINING		
- ACETATE	4.5	4.5
- COTTON	4.5	4.5
- NYLON	4	4
- POLYESTER	4.5	4.5
- ACRYLIC	4.5	4.5
- WOOL	4.5	4.5

03. COLORFASTNESS TO ARTIFICIAL LIGHT : XENON ARC FADING LAMP TEST (AATCC TM16.3-2014e2 : 2014, XENON-ARC-LAMP, GRAY SCALE) : GRADE

	#1	#2
20 AFU	4.5	4.5


NOTE) THE APPARATUS USED : ATLAS WEATHER OMETER

** End of The Report **

e-DOCUMENT SERVICE
The test results contained in this report are limited to results on the sample(s) that is provided by client and are not necessarily indicative or representative of the qualities of the lot from which the sample(s) was taken or of all products. Results contained in this report are not based on the quality certification of sample by the FITI quality certification program unless specifically requested by the client. Further use of the results of this report is prohibited unless allowed under a separate agreement set forth in an official document that is established between the client identified on this letter and the FITI.
This test report is irrelevant to KS Q ISO/IEC 17025 and KOLAS accreditation.

(07791) 79, Magokjungang 8-ro 3-gil, Gangseo-gu, Seoul
Tel : 02-3299-8000 Fax : 02-3299-8153

- SAMPLE PHOTO -



e-DOCUMENT SERVICE

The test results contained in this report are limited to results on the sample(s) that is provided by client and are not necessarily indicative or representative of the qualities of the lot from which the sample(s) was taken or of all products. Results contained in this report are not based on the quality certification of sample by the FITI quality certification program unless specifically requested by the client. Further use of the results of this report is prohibited unless allowed under a separate agreement set forth in an official document that is established between the client identified on this letter and the FITI.
This test report is irrelevant to KS Q ISO/IEC 17025 and KOLAS accreditation.