CÔNG TY CỔ PHẦN - VIỆN NGHIÊN CỨU DỆT MAY
VIETNAM TEXTILE RESEARCH INSTITUTE., JSC (VTRI)
TRUNG TÂM THÍ NGHIỆM DỆT MAY
TEXTILE TESTING CENTRE (TTC)
Add: 478 Minh Khai, Hai Ba Trung, Hanoi, Vietnam
Tel :(84-24) 2 215 6167 / 6 681 5577
Fax: (84-24) 3 862 2867
Email: lab_tri@viendetmay.org.vn
Website: www.viendetmay.org.vn

VILAS 089

TEST REPORT

Report No.: 202-24-05-24/TNPV-1
Date of issue: May 29th, 2024

Client : SHINSUNG VINA COMPANY LIMITED
Address : Lot CN04, Cam Khe Industrial Park, Cam Khe Town, Cam Khe District, Phu Tho Province
Date of sample receipt: May 24th, 2024 Date(s) of performance: From May 24th to May 29th, 2024

Sample provided and identified by client
Sample Identification: Polyester Ply Yarn 1000D/2P_ Natural

Test Sample:

Sample



Test results:

No.	Items		Test Methods	Results
1	Plied yarn twist	Average twist (tpm)	ASTM D1423/D1423M-16(2022)	187
		Cv (%)		3.3
2	Thickness (mm)		ISO 5084:1996	0.36

SIGNED FOR AND ON BEHALF OF VTRI

KT. GIÁM ĐỐC TRUNG TÂM THÍ NGHIỆM
PHÓ GIÁM ĐỐC
ThS. Nguyễn Hữu Đông

VTRI - TTC - VILAS 089 - ISO/IEC 17025

Results are valid for tested samples provided by applicant only: 50 grams.
Reproduction a part of this Test Report is not allowed without permission written of Textile Testing Centre.
Client, Sample identification and Manufacturer are introduced at client's requests. TTC shall not be in charge of information provided by the client: sample identification, sample origin, client name, test requirements...