CÔNG TY CỔ PHẦN - VIỆN NGHIÊN CỨU DỆT MAY
VIETNAM TEXTILE RESEARCH INSTITUTE., JSC (VTRI)

Add: 478 Minh Khai, Hai Ba Trung, Hanoi, Vietnam
Tel :(84-24) 2 215 6167 / 6 681 5577
Fax: (84-24) 3 862 2867
Email: lab_tri@viendetmay.org.vn
Website: www.viendetmay.org.vn

TRUNG TÂM THÍ NGHIỆM DỆT MAY
TEXTILE TESTING CENTRE (TTC)

TEST REPORT

Report No.: 200-24-05-24/TNPV-1
Date of issue: June 5th, 2024

Client : SHINSUNG VINA COMPANY LIMITED

Address : Lot CN04, Cam Khe Industrial Park, Cam Khe Town, Cam Khe District, Phu Tho Province

Date of sample receipt: May 24th, 2024 Date(s) of performance: From June 3rd to June 5th, 2024

Sample provided and identified by client

Sample Identification: Polypropylene Multi filament Yarn 1400D_Natural

Test Sample:

Sample



Test results:

No.	Items		Test Methods	Results
1	Shrinkage of yarns (%)	Boiling water method (1)	ASTM D2259-21	1.6
		Dry-Heat method (2)		7.7

Remark:
(1): Number of specimens: One skein.
(2): Number of specimens: One skein includes 30-warp. The exposure to dry heat: time of the exposure: 2 min; temperature of the exposure: 132 °C.

SIGNED FOR AND ON BEHALF OF VTRI

M.S.D.N: 0100100294 - C.T.C.P
CÔNG TY
CỔ PHẦN -
VIỆN NGHIÊN CỨU
DỆT MAY
Q. HAI BÀ TRƯNG - TP. HÀ NỘI

KT. GIÁM ĐỐC TRUNG TÂM THÍ NGHIỆM
PHÓ GIÁM ĐỐC
ThS. Nguyễn Hữu Đông

VTRI - TTC - VILAS 089 - ISO/IEC 17025

Results are valid for tested samples provided by applicant only: 50 grams.
Reproduction a part of this Test Report is not allowed without permission written of Textile Testing Centre.
Client, Sample identification and Manufacturer are introduced at client's requests. TTC shall not be liable for information made available by the client: sample identification, sample origin, client name, test requirements...